

## DMP-30 epoxy resin curing accelerator



Epoxy resin curing accelerator DMP-30 (K-54), 2,4,6 tri (dimethylaminomethyl) phenol, is a tertiary amine type curing agent. The epoxy curing agent at room temperature for perishable as anhydrides, polyester amines, aliphatic amine curing agent, efficient accelerator.

Typical physical properties:

Appearance: light yellow viscous liquid

Viscosity: MPa · s / 25 °C 60-80

Solid content:%  $\geq$  96

Moisture content:%  $\leq$  0.2

Specific gravity: @ 25 °C 0.98

Applications:

Plus fast curing epoxy potting compound, encapsulation materials, casting materials, adhesives, floor coatings and other.

Packing:

25KG / plastic drum or 200KG / iron drum

Note:

Epoxy curing agent accelerator DMP-30 moderate irritation to the skin and eyes, if contact with skin, wash with soap if contact with eyes, immediately flush with water and seek medical advice.

